



PRODUCT SPECIFICATION SHEET
Ti-6Al-4V Grade 23
-150 μm/+45 μm

CHEMICAL COMPOSITION:


Element	Typical Gr. 23 (% wt.)
Titanium	Balance
Aluminum	5.50 - 6.50
Vanadium	3.50 - 4.50
Carbon	< 0.08
Oxygen	< 0.13
Nitrogen	< 0.03
Hydrogen	< 0.0125
Iron	< 0.25
Other each, max	0.10
Other total, max	0.40

APPARENT DENSITY:


2.60-2.65 g/cm³

HALL FLOWMETER:

21-26 s



PARTICLE SIZE DISTRIBUTION (LASER DIFFRACTION):



d10: 50 μm-55 μm • d50: 75 μm-85 μm • d90: 113 μm-120 μm



PLASMA ATOMIZED

**IDEAL FOR ADDITIVE
MANUFACTURING**

EXCELLENT FLOWABILITY

HIGHLY SPHERICAL

HIGH PACKING DENSITY

LOW POROSITY

LITTLE TO NO SATELLITES

HIGH CHEMICAL PURITY

TSX: PYR • OTCQB: PYRNF

For more information, please contact:

Business Development Department
PyroGenesis Additive

powders@pyrogenesis.com

T. +1 (514) 937-0002

F. +1 (514) 937-5757