



PRODUCT SPECIFICATION SHEET

In-718
-90 μm/+45 μm

CHEMICAL PROPERTIES:


Element	Typical 718 (% wt.)	Element	Typical 718 (% wt.)
Aluminum	0.61	Niobium	5.14
Bore	<0.005	Nickel	54.17
Cobalt	0.17	Phosphorus	0.005
Carbon	0.02	Sulfur	< 0.001
Oxygen	0.01	Silicon	0.07
Nitrogen	0.01	Titanium	0.97
Hydrogen	0.0004	Vanadium	0.04
Iron	18.15	Tungsten	0.03
Manganese	0.07	Copper	0.04
Chromium	17.6	Molybdenum	2.89

APPARENT DENSITY:


4.65 - 4.80 g/cm³

HALL FLOWMETER:

12-14 s



PARTICLE SIZE DISTRIBUTION (LASER DIFFRACTION):



d10: 42 μm-46 μm • d50: 60 μm-65 μm • d90: 85 μm-90 μm



PLASMA ATOMIZED

IDEAL FOR ADDITIVE MANUFACTURING

EXCELLENT FLOWABILITY

HIGHLY SPHERICAL

HIGH PACKING DENSITY

LOW POROSITY

FEW SATELLITES

HIGH CHEMICAL PURITY

TSXV: PYR • OTCQB: PYRNF

For more information, please contact:

Business Development Department
PyroGenesis Additive

powders@pyrogenesis.com

T. +1 (514) 937-0002

F. +1 (514) 937-5757

© 2018, PYROGENESIS ADDITIVE
THE DRAWINGS AND INFORMATION DEPICTED HEREIN ARE PROPRIETARY TO PYROGENESIS ADDITIVE THEY MAY NOT BE COPIED, REPRODUCED, TRANSMITTED, DISCLOSED, SOLD, ALTERED OR OTHERWISE USED IN WHOLE OR IN PART IN ANY MANNER WHATSOEVER, INCLUDING AS BASIS FOR DESIGN, MANUFACTURE OR SALE OF PRODUCTS, WITHOUT PRIOR WRITTEN CONSENT OF PYROGENESIS ADDITIVE.