



PRODUCT SPECIFICATION SHEET
Ti-6Al-4V GRADE 23
-106 μm/+45 μm

CHEMICAL COMPOSITION:


Element	Typical Gr. 23 (% wt.)
Titanium	Balance
Aluminum	5.50 - 6.50
Vanadium	3.50 - 4.50
Carbon	< 0.08
Oxygen	< 0.13
Nitrogen	< 0.03
Hydrogen	< 0.0125
Iron	< 0.25
Other each, max	0.10
Other total, max	0.40

APPARENT DENSITY:


2.51-2.65 g/cm³

HALL FLOWMETER:

21-28 s



PARTICLE SIZE DISTRIBUTION (LASER DIFFRACTION):



d10: 38 μm-43 μm • **d50: 54 μm-61 μm** • **d90: 82 μm-84 μm**



PLASMA ATOMIZED

**IDEAL FOR ADDITIVE
 MANUFACTURING**

EXCELLENT FLOWABILITY

HIGHLY SPHERICAL

HIGH PACKING DENSITY

LOW POROSITY

FEW SATELLITES

HIGH CHEMICAL PURITY

TSXV: PYR • OTCQB: PYRNF

For more information, please contact:

Business Development Department
PyroGenesis Additive

powders@pyrogenesis.com

T. +1 (514) 937-0002

F. +1 (514) 937-5757

© 2018, PYROGENESIS ADDITIVE
 THE DRAWINGS AND INFORMATION DEPICTED HEREIN ARE PROPRIETARY TO PYROGENESIS ADDITIVE THEY MAY NOT BE COPIED, REPRODUCED, TRANSMITTED, DISCLOSED,
 SOLD, ALTERED OR OTHERWISE USED IN WHOLE OR IN PART IN ANY MANNER WHATSOEVER, INCLUDING AS BASIS FOR DESIGN, MANUFACTURE OR SALE OF PRODUCTS,
 WITHOUT PRIOR WRITTEN CONSENT OF PYROGENESIS ADDITIVE.